



SUPEARL

1512 HQH

Description

SUPEARL 1512 HQH is a white opaque, cavitated, BOPP film designed for label applications, preferably for In-Mould Labelling (IML). One side glossy and other side matt, both sides treated.

It is specially designed for In-Mould Labelling (IML) for PP and PE based injection moulding applications. It is suitable for gravure, flexo, UV & oxidative offset, letterpress and screen printing.

Specifically designed for large containers and buckets to eliminate present IML process problems such as distortions.

Any possible caution for blocking tendency during printing and/or other processes should be taken since the film is both sides treated.

Properties

- Excellent web flatness and good dimensional stability
- Glossy effect without orange peel effect
- Excellent die cutting properties
- Applicable for sheet-fed applications
- Required level of anti-static properties at all processes
- Excellent ink adhesion
- Resistance to chemicals, greases, oil, fruit acid and sugar

Technical Features

PROPERTIES	TEST METHOD	UNITS	1512 HQH	
THICKNESS	ASTM F2251	micron	60	70
		Gauge	240	280
YIELD	ASTM D4321	m ² /kg	19,2	16,4
		in ² /Lbs	13.500	11.500
UNIT WEIGHT	ASTM D4321	g/m ²	52,2	60,9
GLOSS (45 °) (*)	ASTM D2457	%	15	
LIGHT TRANSMISSION	ASTM D1746	%	30	25
OPACITY	DIN 53146	%	75	80
TENSILE STRENGTH AT BREAK	ASTM D882	MD	N/mm ²	110
			lb/in ²	16.000
		TD	N/mm ²	230
			lb/in ²	33.400
ELONGATION AT BREAK	ASTM D882	MD	%	200
		TD	%	60
THERMAL SHRINKAGE (120 °C, 5 min, air)	ASTM D1204	MD	%	3
		TD	%	1
COEFFICIENT OF FRICTION	ASTM D1894	Film/Film	0,30	
		Film/Metal	0,20	
SURFACE TENSION	ASTM D2578	Dyne/cm	Glossy Side	38
			Matt Side	38

“Product Identification (Decision 97/129/EC): PP5”

(*) Matt surface

Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intended to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

For related spec sheet with tolerance values, please contact our sales departments

STANDARD ROLL DIMENSIONS			
CORE INNER DIAMETER (ID)	CORE OUTER DIAMETER (OD)	LENGTH TOLERANCE	WIDTH TOLERANCE
76 mm (3 in) & 152 mm (6 in)	530 mm & 790 mm *	± % 5 for ≤ 390 mm OD ± % 10 for > 390 mm OD	- 0 & + 4 mm

* 790 mm OD is available for BOPP films above 350 mm width

Rev: 04 Date: 16.11.2022